

UltraTape



Reinraum-Klebeband PVC Surface-Protection

#0315-1

pure¹¹-Nr. : 1130025 , Marke : UltraTape

Eigenschaften

- Marke: UltraTape
- Breite in cm: 2 cm
- Klebestärke: leicht
- Klebstoff: Acryl
- PVC: 100 %
- Rückstandsfrei ablösbar

Empfohlene Reinraumklassen

ISO 7 | 8 | 9

GMP C | D

Material

-

Verpackung

- STK

pure¹¹ GmbH

Bavariafilmplatz 7 | D-82031 Grünwald

Geschäftsführer: Julian Kropp

AG München HRB 171307

T +49 89 5589434 0

F +49 89 5589434 77

www.pure11.de

info@pure11.de

Produktvarianten

pure¹¹-Nr.: 1130025TP1I, Reinraum-Klebeband PVC Surface-Protection #0315-1

Farbe: Transparent; Breite: 1" / VE: STK

pure¹¹ GmbH

Bavariafilmplatz 7 | D-82031 Grünwald

Geschäftsführer: Julian Kropp

AG München HRB 171307

T +49 89 5589434 0

F +49 89 5589434 77

www.pure11.de

info@pure11.de

UT1315 Vinyl Surface Protection Low Adhesion Cleanroom Tape

DESCRIPTION

UltraTape 1315 / 0315 is designed to provide maximum protection to surfaces such as stainless steel, glass, aluminum coated metal and plastics while allowing for easy clean removal. Designed for cleanroom use.

- Protects surfaces during processing, storage or shipping
- Low adhesion, easy clean removal without residue
- Available in almost any width
- Cleanroom certified

PROPERTIES

Backing	PVC
Adhesive	Acrylic
Total Thickness	2.95 mils (0.075 mm)
Adhesion to Stainless Steel	0.89 N/20mm
Elongation	258 %
Unwinding Force	0.23 N/20mm
Tensile Strength	63 N/20mm
Length	55 yards
Colors	Transparent Blue (TB)

To achieve ultimate adhesion, the bonding surface should be clean, dry, and free of dirt and oils. The strength of the adhesive bond is dependent on the amount of surface area directly in contact with the adhesive. Firm pressure is recommended to achieve good adhesive to surface contact.

UltraTape recommends that each user conduct their own test to determine the product's suitability for the intended application and shall assume all risks and liabilities in connection therewith. Materials should be stored at 70 °F (21C°) with 50% relative humidity.