

UltraTape



Reinraum-Klebeband Polyester High-Temp #6573-1

pure¹¹-Nr. : 1130035 , Marke : UltraTape

Eigenschaften

- Marke: UltraTape
- Material: Polyester
- Breite in cm: 2 cm
- Länge in m: 65,83
- Autoklavierbar
- Chemikalienbeständigkeit
- Klebestärke: leicht
- Klebstoff: Silikon
- Polyester/PES: 100 %
- Reinheitsgrad: Ultrac Clean
- Rückstandsfrei ablösbar
- Temperaturbeständig

Empfohlene Reinraumklassen

ISO 4 | 5 | 6 | 7 | 8 | 9

GMP A/B | C | D



Material

- Polyester

Verpackung

- 6STK

pure¹¹ GmbH

Bavariafilmplatz 7 | D-82031 Grünwald

Geschäftsführer: Julian Kropp

AG München HRB 171307

T +49 89 5589434 0

F +49 89 5589434 77

www.pure11.de

info@pure11.de

Produktvarianten

pure¹¹-Nr.: 1130035GN1I, Reinraum-Klebeband Polyester High-Temp #6573-1

Farbe: Grün; Breite: 1" / VE: 6STK

pure¹¹ GmbH

Bavariafilmpfad 7 | D-82031 Grünwald

Geschäftsführer: Julian Kropp

AG München HRB 171307

T +49 89 5589434 0

F +49 89 5589434 77

www.pure11.de

info@pure11.de

UT6573 Green High Temp Polyester Cleanroom Tape

DESCRIPTION

UltraTape 6573 / 0573 is a high temperature polyester masking tape with silicone adhesive which removes cleanly from most surfaces. The stiff polyester backing resists curling for masking surfaces.

- Removes with no adhesive residue
- High temperature masking
- Bonds to low energy surfaces
- Cleanroom certified

PROPERTIES

Backing	Polyester
Adhesive	Silicone
Backing Thickness	1.0 mil (0.0254 mm)
Adhesive Thickness	0.9 mil (0.02286 mm)
Adhesion to Stainless	14 oz/in (3.89 N/25.4 mm)
Operating Temperature	-40°F to 425°F (-40°C to 219°C)
Tensile Strength	24 lbs./in (106.76 N/25.4mm)
Length	72 yards
Colors	Green (GR)

To achieve ultimate adhesion, the bonding surface should be clean, dry, and free of dirt and oils. The strength of the adhesive bond is dependent on the amount of surface area directly in contact with the adhesive. Firm pressure is recommended to achieve good adhesive to surface contact.

UltraTape recommends that each user conduct their own test to determine the product's suitability for the intended application and shall assume all risks and liabilities in connection therewith. Materials should be stored at 70°F (21°C) with 50% relative humidity.