



Tuchrolle Sontara EC White

pure¹¹-Nr.: 06066, Hersteller: Jacob Holm

Zusammenfassung

- Neue pure11-Artikelnummer (ab 01.07.2023): 1106066
- Material: Holzzellstoff 50,4% / PET 49,6% (Sontara EC White)
- Gewicht: 73 g/m²
- Sehr gute Reißfestigkeit
- Hohe Absorptionskraft
- Extrem widerstandsfähig und langlebig
- Sehr gute Bestandfähigkeit gegen Lösungs- und Reinigungsmittel
- Exzellente Eignung zum Polieren und Finishing
- 400 Tücher pro Rolle
- Lieferform: auf Rolle

Empfohlene Reinraumklassen

ISO	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>
GMP	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input checked="" type="checkbox"/>	<input type="checkbox"/>

Produktvarianten

pure¹¹-Nr.: **060663138**

Farbe: Weiß / Maße: 31 x 38 cm (12 x 15") / Herst.-Nr.: D13402245 / VE: 1 Rolle

Quelle: <https://www.pure11.de/tuchrolle-sontara-ec-white>

STYLE K949S

50.4% Woodpulp – 49.6% PET

White

Creped Smooth

TYPICAL MATERIAL PROPERTIES

Test	Orientation	Units	Value	Method
Basis Weight		g/m ²	73	WSP 130.1
Thickness		mm	0.53	WSP 120.6
Absorption Capacity		%	585	WSP 10.1
Extrinsic Absorption Capacity		ml/m ²	422	WSP 10.2
Grab Tensile Strength	MD	N/4in	142	ASTM D5034
	CD	N/4in	73	
Strip Tensile Strength	MD	N/5cm	135	WSP 110.4
	CD	N/5cm	55	

These are not specifications and only to be used as indicative properties. All properties are typical values according to our current knowledge at the time of the last update of this publication. They are given for general guidance only – Jacob Holm does not warrant any results and assumes no obligation or liability whatsoever in connection with this information. Please conduct your own tests to ensure consistency for your applications. The publication of these properties does not grant any right or license to any intellectual property of Jacob Holm. MD = machine direction, CD = cross direction – Data last updated March 16, 2017 ©2017 Jacob Holm & Sons AG. All rights reserved.