




Nitril-Handschuhe PUREZERO HG3 (white)

pure¹¹-Nr.: 05011, Hersteller: HALYARD



Zusammenfassung

- Neue pure11-Artikelnummer (ab 01.07.2023): 1105011
- Material: Nitril
- Beidhändig tragbar
- Puderfrei
- Latexfrei
- AQL-Wert (Acceptable Quality Level): 1.5
- Texturierte Fingerspitzen
- Ausgezeichnetes Fingerspitzengefühl und hohe Tastempfindlichkeit
- Sicherer Halt durch gute Griffigkeit
- Vulkanisationsbeschleunigerfrei
- Mehrfach in deionisiertem Wasser gewaschen
- Beständig gegen eine Vielzahl von Zytostatika
- Statisch dissipatives Verhalten im Gebrauch, getestet nach EN 1149
- Doppelt unterverpackt

Empfohlene Reinraumklassen

ISO

3 4 5 6 7 8 9

GMP

C D

Produktvarianten

pure¹¹-Nr.: 05011XS

Farbe: Weiß / Größe: XS / Herst.-Nr.: CLN3031XS / VE: 1.000 Stück

pure¹¹-Nr.: 05011S

Farbe: Weiß / Größe: S / Herst.-Nr.: CLN3031SM / VE: 1.000 Stück

pure¹¹-Nr.: 05011M

Farbe: Weiß / Größe: M / Herst.-Nr.: CLN3031MD / VE: 1.000 Stück

pure¹¹-Nr.: 05011L

Farbe: Weiß / Größe: L / Herst.-Nr.: CLN3031LG / VE: 1.000 Stück

pure¹¹-Nr.: 05011XL

Farbe: Weiß / Größe: XL / Herst.-Nr.: CLN3031XL / VE: 1.000 Stück

Quelle: <https://www.pure11.de/nitril-handschuhe-purezero-hg3-white>

TECHNISCHES DATENBLATT

Beschreibung

Die weißen HALYARD* **PUREZERO*** HG3 Reinraumhandschuhe aus Nitril dienen dem Gebrauch bei der Herstellung von Halbleiter-, Arzneimittel- und Medizinprodukten. Diese Handschuhe werden einem Reinheitsverfahren unterzogen (mehrfach in deionisiertem Wasser gewaschen), um eine konsistente Kontrolle geringfügiger Partikel und extrahierbarer Substanzen zu gewährleisten und werden für den Gebrauch in Reinraumumgebungen der ISO-Klasse 3 oder darüber empfohlen. Da die weißen HALYARD* **PUREZERO*** Nitrilhandschuhe **ohne Beschleuniger** gefertigt werden, besteht ein geringeres Allergie- und Hautirritationsrisiko als bei beschleunigerhaltigen Nitrilhandschuhen.



	XS	S	M	L	XL
Handschuhlänge (cm):	30,5	30,5	30,5	30,5	30,5
Länge Mittelfinger (cm)	7,1	7,85	8,05	8,81	9,16
Breite Handfläche (mm)	70	80	95	110	120
Dicke Fingerspitze	0,16 mm	0,16 mm	0,16 mm	0,16 mm	0,16 mm
Dicke Handfläche	0,13 mm	0,13 mm	0,13 mm	0,13 mm	0,13 mm
Dicke Handschuhbund	0,10 mm	0,10 mm	0,10 mm	0,10 mm	0,10 mm

Physikalische Eigenschaften

AQL	1,5
Unsteril	✓
Beidhändig tragbar	✓
Griffige Oberflächenbeschaffenheit	✓
Texturierte Fingerspitzen	✓
Beschleunigerfrei	✓
Latexfrei	✓
Puderfrei	✓
Silikonfrei	✓
Reißfestigkeit*	20 MPa (Zielwert)
Maximale Dehnung*	600%
Haltbarkeit	3 Jahre

TECHNISCHES DATENBLATT

Reinheit

Max. Partikelzahl	>0,5µm / cm ² <950	IEST RP-CC005
Ionengehalt (Extrahierbare Ionen)	Max. Gehalt (ug/g)	IEST RP-CC005
Calcium	50	
Chlorid	35	
Magnesium	5	
Nitrat	20	
Kalium	5	
Natrium	10	
Sulfat	10	
Zink	25	
Ammonium	5	

Verpackung

Doppelbeutel plus Schutzhülle

1000 Handschuhe pro Kiste: 100 Handschuhe pro PE-Beutel X 10 PE-Beutel pro ausgekleidetem Karton

Im Reinraum der ISO-Klasse 5 verpackt

Qualitäts- und Regulierungsstandards

Entspricht diesen regulatorischen Normen:

ISO 9001
ISO 13485

Entspricht diesen regulatorischen Normen zum Umgang mit Lebensmitteln:

FDA 21 CFR 177-2600
Verordnung (EU) 10/2011 der Kommission
Japanisches Lebensmittelhygienegesetz

Akkreditiert gemäß FDA 21 CFR Abschnitt 820

CE 2797 PSA-Kategorie III gemäß EU-Verordnung 2016/425 EWG

EN ISO 374-5:2016 Virusschutz
EN ISO 374-1:2016/Typ C K - Geringer Chemikalienschutz
EN 420:2003 +A1:2009



Weitere Informationen

Empfohlen für den Gebrauch in Reinräumen der ISO-Klasse 3 oder darüber

Hergestellt in Thailand

Konformitätserklärung und Analysenzertifikate
für jede Charge abrufbar unter:
[.halyardhealth.com/information](https://www.halyardhealth.com/information)

Hergestellt in unserer
Produktionsstätte Safeskin Medical
& Scientific (Thailand) Ltd.

Bestellinformation

HALYARD* PUREZERO* HG3 Nitrilhandschuhe, weiß,
unsteril, beidhändig tragbar, griffige Beschaffenheit

XS	CLN3031XS
SM	CLN3031SM
MD	CLN3031MD
LG	CLN3031LG
XL	CLN3031XL

Weitere Informationen oder
Muster erhalten Sie über Ihren
lokalen Vertriebshändler oder
unter www.halyardhealth.de

1. IDENTIFICATION

Product Name: ***HALYARD* PUREZERO* HG3 Nitrile Gloves***

Product Number: Various

Date Prepared:	6/24/2021
Manufacturer:	O&M Halyard, Inc. 1 Edison Dr. Alpharetta, Georgia 30005
Telephone: MEDICAL EMERGENCY: TRANSPORTATION EMERGENCY: INFORMATION:	Call 911 or your local Emergency Room or Poison Control Services Chemtrec 1-800-424-9300 or 1-703-527-3887 (collect calls accepted) 1-844-HALYARD

Product Use: Protective gloves.

2. HAZARDS IDENTIFICATION

GHS Classification: Not Hazardous. These products are manufactured articles or articles as this term is defined in the OSHA Hazard Communication Standard (20CFR 1910.1200), EU REACH, Canadian WHMIS, Australia WHS and the GHS. These products are out of the scope of the GHS and no SDS or labeling are required.

GHS Labeling: No GHS labeling required.

3. COMPOSITION/INFORMATION ON INGREDIENTS

<i>Chemical Name</i>	<i>CAS-No./ EINECS-No</i>	<i>%</i>	<i>GHS Classification:</i>
Non-Hazardous Ingredients	Mixture	100	Not Hazardous

4. FIRST AID MEASURES

Inhalation: No first aid needed.

Skin contact: No first aid needed. These products are intended to be used in contact with the skin.

Eye contact: No first aid needed.

Ingestion: Not a relevant route of exposure.

Most Important symptoms and effects, both acute and delayed: No adverse effects.

Indication of any immediate medical attention and special treatment needed: None required.

5. FIRE-FIGHTING MEASURES

Suitable (and unsuitable) Extinguishing Media: Use media suitable for surrounding materials.

Specific Hazards Arising from the Chemical: These products can melt in a fire. Molten material may flow or drip and spread the fire.

Hazardous Combustion Products: Combustion may produce toxic and irritating gases and vapors.

Special Protective Equipment and Precautions for Fire-fighters: None required.

6. ACCIDENTAL RELEASE MEASURES

Personal Precautions, Protective Equipment, and Emergency Procedures: None required.

Environmental Precautions: None required.

Methods and Materials for Containment and Cleaning Up: No special precautions required. Pick up and dispose of in an appropriate container.

7. HANDLING AND STORAGE

Precautions for Safe Handling: No special handling is required.

Conditions for Safe Storage, including any Incompatibilities: Store away from heat and flames.

8. EXPOSURE CONTROLS / PERSONAL PROTECTION**Exposure limit(s)**

Chemical Name	Exposure limit(s)
Non-Hazardous Ingredients	None established

Appropriate Engineering Controls: None required.

Individual Protection Measures, such as Personal Protective Equipment:

Respiratory Protection: None required.

Protective Gloves: None required.

Eye Protection: None required.

9. PHYSICAL AND CHEMICAL PROPERTIES

Appearance and Odor	Solid Gloves, blue or white
Odor Threshold:	Not applicable
Boiling point/range	Not applicable
Melting point/range	Not determined
Relative Density (water=1)	Not determined
Vapor pressure	Not applicable
Vapor density (air=1)	Not applicable
Solubility	Insoluble
pH	Not applicable
Partition coefficient (n-octanol/water):	Not applicable
Evaporation Rate (Butyl acetate=1)	Not applicable
Viscosity:	Not applicable
Volatile Organic Carbon Compounds (VOC) (g/L)	Not applicable
Flashpoint:	None.
Flammable Limits in Air % by Volume:	LEL (Lower):Not applicable UEL (Upper): Not applicable
Autoignition temperature:	Not determined.
Decomposition temperature:	Not determined
Flammability (solid, gas):	Not a flammable solid

10. STABILITY AND REACTIVITY

Reactivity: Not reactive.

Chemical Stability: Stable at ambient temperature and pressure.

Possibility of Hazardous Reactions: None known.

Conditions to Avoid: Avoid heat and flames.

Incompatible Materials: None known.

Hazardous Decomposition Products: Thermal decomposition may produce carbon and nitrogen oxides and unidentified hydrocarbon fragments.



11. TOXICOLOGICAL INFORMATION

Symptoms/Effects of Overexposure: These gloves are manufactured articles. Their use will not result in exposure to any hazardous materials.

Inhalation: Not applicable.

Skin contact: None. Intended for skin contact. These products contain no natural latex.

Eye contact: None expected.

Ingestion: Not applicable.

Chronic toxicity: None expected.

Carcinogenicity Data: None of the components of this product is listed as a carcinogen by IARC, NTP, US OSHA or the EU CLP Annex VI.

Reproductive Toxicity: None known.

Numerical Measures of Toxicity:
Not acutely toxic.

12. ECOLOGICAL INFORMATION

Ecotoxicity: These gloves are manufactured articles. Their use will not result in adverse environmental effects.

Persistence and Degradability: Not degradable.

Bioaccumulative Potential: Not bioaccumulative.

Mobility in Soil: Not mobile.

Other Adverse Effects: None currently known.

13. DISPOSAL CONSIDERATIONS

Dispose in accordance with all state, local and federal regulations. If unused, the product may be disposed of as a non-hazardous material.

14. TRANSPORT INFORMATION

US DOT Shipping Description: Not regulated

IATA Shipping Description (Air): Not regulated

IMDG Shipping Description (Vessel): Not regulated

15. REGULATORY INFORMATION

US Regulations

EPA Toxic Substances Control Act (TSCA): These gloves are articles and exempt from the TSCA regulations.



SARA 302 Listed Chemicals: None.

SARA 311/312 Hazard Categories: Not applicable to articles

SARA 313 This Product Contains the Following Chemicals Subject to Annual Release Reporting Requirements Under the SARA Section 313 (40 CFR 372): Not applicable to articles.

16. OTHER INFORMATION

Date Prepared: 6/24/2021

HMIS Rating: Health 0 Fire 1 Physical Hazard 0

The information contained herein is true and correct to the best of O&M Halyard, Inc's knowledge. However, no warranty, expressed or implied, is made. Nothing herein should be interpreted as a recommendation to infringe existing patents or violate any laws or regulations. Final determination of the suitability of the material is the sole responsibility of the user.



February 8th, 2021

RE: HALYARD* PUREZERO* HG3 Nitrile Gloves

Dear Valued Customer,

This letter is in response to your recent inquiry regarding the chemotherapy drugs tested on HALYARD* PUREZERO* HG3 Nitrile Gloves.

The results below reflect a comprehensive list of chemotherapy drugs tested on HALYARD* PUREZERO* HG3 Nitrile Gloves with indicated breakthrough time in accordance with **ASTM D6978**, *Standard Practice for Assessment of Resistance of Medical Gloves to Permeation by Chemotherapy Drugs*.

HALYARD* PUREZERO* HG3 Light Blue Nitrile Gloves (Sterile and Non-Sterile)

	Chemotherapy Drug and Concentration	Min. Breakthrough Time (Minutes)
1	Cisplatin (1.0 mg/ml)	No breakthrough up to 240 minutes
2	Cyclophosphamide (Cytoxan) (20.0 mg/ml)	No breakthrough up to 240 minutes
3	Dacarbazine (10.0 mg/ml)	No breakthrough up to 240 minutes
4	Doxorubicin HCl (2.0 mg/ml)	No breakthrough up to 240 minutes
5	Etoposide (20.0 mg/ml)	No breakthrough up to 240 minutes
6	Fluorouracil (50.0 mg/ml)	No breakthrough up to 240 minutes
7	Ifosfamide (50.0 mg/ml)	No breakthrough up to 240 minutes
8	Mitoxantrone (2.0 mg/ml)	No breakthrough up to 240 minutes
9	Paclitaxel (6.0 mg/ml)	No breakthrough up to 240 minutes
10	Vincristine Sulfate (1.0 mg/ml)	No breakthrough up to 240 minutes
11	Carmustine (3.3 mg/ml)	Breakthrough detected at 87.9 minutes
12	ThioTEPA (10.0 mg.ml)	Breakthrough detected at 109.1 minutes

HALYARD* PUREZERO* HG3 White Nitrile Gloves (Sterile and Non-Sterile)

	Chemotherapy Drug and Concentration	Min. Breakthrough Time (Minutes)
1	Cisplatin (1.0 mg/ml)	No breakthrough up to 240 minutes
2	Cyclophosphamide (Cytoxan) (20.0 mg/ml)	No breakthrough up to 240 minutes
3	Dacarbazine (10.0 mg/ml)	No breakthrough up to 240 minutes
4	Doxorubicin HCl (2.0 mg/ml)	No breakthrough up to 240 minutes
5	Etoposide (20.0 mg/ml)	No breakthrough up to 240 minutes
6	Fluorouracil (50.0 mg/ml)	No breakthrough up to 240 minutes
7	Ifosfamide (50.0 mg/ml)	No breakthrough up to 240 minutes
8	Mitoxantrone (2.0 mg/ml)	No breakthrough up to 240 minutes
9	Paclitaxel (6.0 mg/ml)	No breakthrough up to 240 minutes
10	Vincristine Sulfate (1.0 mg/ml)	No breakthrough up to 240 minutes
11	Carmustine (3.3 mg/ml)	Breakthrough detected at 99.0 minutes
12	ThioTEPA (10.0 mg/ml)	Breakthrough detected at 179.8 minutes

HALYARD* PUREZERO* SMOOTH HG3 White Nitrile Gloves

	Chemotherapy Drug and Concentration	Min. Breakthrough Time (Minutes)
1	Cisplatin (1.0 mg/ml)	No breakthrough up to 240 minutes
2	Cyclophosphamide (Cytoxan) (20.0 mg/ml)	No breakthrough up to 240 minutes
3	Dacarbazine (10.0 mg/ml)	No breakthrough up to 240 minutes
4	Doxorubicin HCl (2.0 mg/ml)	No breakthrough up to 240 minutes
5	Etoposide (20.0 mg/ml)	No breakthrough up to 240 minutes
6	Fluorouracil (50.0 mg/ml)	No breakthrough up to 240 minutes
7	Ifosfamide (50.0 mg/ml)	No breakthrough up to 240 minutes
8	Mitoxantrone (2.0 mg/ml)	No breakthrough up to 240 minutes
9	Paclitaxel (6.0 mg/ml)	No breakthrough up to 240 minutes
10	Vincristine Sulfate (1.0 mg/ml)	No breakthrough up to 240 minutes
11	Carmustine (3.3 mg/ml)	WARNING: Breakthrough detected at 18.1 minutes
12	ThioTEPA (10.0 mg/ml)	Breakthrough detected at 89.3 minutes

CAUTION: The testing conditions used are intended to approximate the worst-case conditions for clinical use. Testing was conducted on a single layer glove material. It is the user's responsibility to demonstrate the applicability of these gloves for their intended use with chemotherapy drugs.



Thank you for your interest in Halyard products. If you have any questions or need additional information, please do not hesitate to contact us at PIQ@hyh.com or call us directly at (844) 425-9273.

Sincerely,

A handwritten signature in black ink, appearing to read 'S.D.' with a long horizontal flourish extending to the right.

Steven Dowdley
Associate Director of Regulatory Affairs
Global Products
O&M Halyard, Inc.

A handwritten signature in black ink, appearing to read 'Ryan Solan' in a cursive style.

Ryan Solan
R&D Senior Engineer
Global Research and Development
O&M Halyard, Inc.

*Registered Trademark or Trademark of O&M Halyard or its affiliates. ©2021. All rights reserved.



August 31st, 2021

RE: HALYARD* PUREZERO* HG3 Nitrile Gloves

Dear Valued Customer,

This letter is in response to your recent inquiry regarding ESD testing of **HALYARD* PUREZERO* HG3 Nitrile Gloves**.

The following HALYARD* PUREZERO* HG3 Nitrile Glove families have been tested against **ANSI/ESD SP15.1-2011 "In-Use Resistance Testing of Gloves and Finger Cots"**:

HALYARD* PUREZERO* HG3 White Nitrile Gloves
HALYARD* PUREZERO* HG3 Light Blue Nitrile Gloves
HALYARD* PUREZERO* HG3 Sterile White Nitrile Gloves
HALYARD* PUREZERO* HG3 Sterile Light Blue Nitrile Gloves
HALYARD* PUREZERO* SMOOTH HG3 White Nitrile Gloves

Based on the ANSI/ESD SP15.1-2011 test results from an external laboratory at conditions of 12% RH and 23°C, all five HALYARD* PUREZERO* HG3 Nitrile Glove product families listed above are within the dissipative classification range (Resistance = 10^4 to 10^{11} ohms) as defined by ANSI/ESD standards. Therefore, **HALYARD* PUREZERO* HG3 Nitrile Gloves** are considered to be static dissipative in-use.

Please note that this is based on a standardized test method in a laboratory environment, and the resistance test results and classification do not fully characterize the glove for all electrostatic properties. Other electrostatic properties, such as charge accumulation, and specific process conditions may need to be assessed based on your particular application prior to use.

Thank you for your interest in Halyard products. If you have any questions or need additional information, please do not hesitate to contact us at PIQ@hyh.com or call us directly at (844) 425-9273.

Sincerely,

Steven Dowdley
Director of Regulatory Affairs
Global Products
O&M Halyard, Inc.

Ryan Solan
R&D Senior Engineer
Global Research and Development
O&M Halyard, Inc.

*Registered Trademark or Trademark of O&M Halyard or its affiliates. ©2021. All rights reserved.



July 14th, 2021

RE: HALYARD* PUREZERO* HG3 Nitrile Gloves

Dear Valued Customer,

This letter is in response to your recent inquiry regarding EN 1149 testing on **HALYARD* PUREZERO* HG3 Nitrile Gloves**.

The data provided on the following pages reflect the test results of **HALYARD* PUREZERO* HG3 Nitrile Gloves** for electrostatic properties in accordance with **EN 1149-1:2006** *“Protective Clothing - Electrostatic Properties - Part 1: Test Method for Measurement of Surface Resistivity”* and **EN 1149-3:2004 (Method 2)** *“Protective Clothing - Electrostatic Properties - Part 3: Test Method for Measurement of Charge Decay”*.

The tests were performed at Intertek Testing Services in the UK with a report issuance of 05.07.2021.

Description of the Tested Gloves:

SAMPLE A - HALYARD* PUREZERO* HG3 Sterile White Nitrile Gloves

SAMPLE B - HALYARD* PUREZERO* HG3 White Nitrile Gloves

SAMPLE C - HALYARD* PUREZERO* HG3 Sterile Light Blue Nitrile Gloves

SAMPLE D - HALYARD* PUREZERO* SMOOTH HG3 White Nitrile Gloves

SAMPLE E - HALYARD* PUREZERO* HG3 Light Blue Nitrile Gloves

SAMPLE A - HALYARD* PUREZERO* HG3 Sterile White Nitrile Gloves

Surface Resistivity Test (EN 1149-1: 2006)		
Sample A		
Determination of Surface Resistivity		
The surface resistivity of 5 areas across the sample was determined according to the method specified in BS EN 1149-1: 2006		
Surface	Surface Resistance (Ω)	Surface Resistivity (Ω)
Face	1.1×10^{12}	2.2×10^{13}
Face	1.7×10^{12}	3.4×10^{13}
Face	1.9×10^{12}	3.8×10^{13}
Face	1.0×10^{12}	2.0×10^{13}
Face	1.4×10^{12}	2.8×10^{13}
Mean	1.4×10^{12}	2.7×10^{13}
Reverse	1.3×10^{12}	2.6×10^{13}
Reverse	1.9×10^{12}	3.8×10^{13}
Reverse	2.4×10^{12}	4.8×10^{13}
Reverse	2.1×10^{12}	4.2×10^{13}
Reverse	1.8×10^{12}	3.6×10^{13}
Mean	1.9×10^{12}	3.7×10^{13}
Note: The fabric was not subjected to a pre-wash due to being intended for single use only.		

Induction Decay Test (EN 1149-3: 2004 Method 2)		
Determination of Induction Decay Time		
	Shielding Factor (S)	Half Decay Time t_{50} (Secs)
1	0.00	21.50
2	0.00	20.15
3	0.00	>30.00
Mean	0.00	≥ 23.88
Note: The fabric was not subjected to a pre-wash due to being intended for single use only.		

SAMPLE B - HALYARD* PUREZERO* HG3 White Nitrile Gloves

**Surface Resistivity Test (EN 1149-1: 2006)
Sample B**

Determination of Surface Resistivity

The surface resistivity of 5 areas across the sample was determined according to the method specified in BS EN 1149-1: 2006

Surface	Surface Resistance (Ω)	Surface Resistivity (Ω)
Face	5.3×10^{11}	1.0×10^{13}
Face	5.1×10^{11}	1.0×10^{13}
Face	5.9×10^{11}	1.2×10^{13}
Face	5.9×10^{11}	1.2×10^{13}
Face	6.4×10^{11}	1.3×10^{13}
Mean	5.7×10^{11}	1.1×10^{13}
Reverse	7.6×10^{11}	1.5×10^{13}
Reverse	7.4×10^{11}	1.5×10^{13}
Reverse	6.8×10^{11}	1.3×10^{13}
Reverse	6.4×10^{11}	1.3×10^{13}
Reverse	6.6×10^{11}	1.3×10^{13}
Mean	6.9×10^{11}	1.4×10^{13}

Note: The fabric was not subjected to a pre-wash due to being intended for single use only.

Induction Decay Test (EN 1149-3: 2004 Method 2)

Determination of Induction Decay Time

	Shielding Factor (S)	Half Decay Time t_{50} (Secs)
1	0.01	12.50
2	0.01	6.96
3	0.00	8.86
Mean	0.01	9.42

Note: The fabric was not subjected to a pre-wash due to being intended for single use only.

SAMPLE C - HALYARD* PUREZERO* HG3 Sterile Light Blue Nitrile Gloves

**Surface Resistivity Test (EN 1149-1: 2006)
Sample C**

Determination of Surface Resistivity

The surface resistivity of 5 areas across the sample was determined according to the method specified in BS EN 1149-1: 2006

Surface	Surface Resistance (Ω)	Surface Resistivity (Ω)
Face	2.4×10^{12}	4.8×10^{13}
Face	2.1×10^{12}	4.2×10^{13}
Face	1.8×10^{12}	3.6×10^{13}
Face	2.6×10^{12}	5.1×10^{13}
Face	2.5×10^{12}	5.0×10^{13}
Mean	2.3×10^{12}	4.5×10^{13}
Reverse	1.7×10^{12}	3.4×10^{13}
Reverse	2.1×10^{12}	4.2×10^{13}
Reverse	2.8×10^{12}	5.5×10^{13}
Reverse	2.0×10^{12}	4.0×10^{13}
Reverse	2.4×10^{12}	4.8×10^{13}
Mean	2.2×10^{12}	4.3×10^{13}

Note: The fabric was not subjected to a pre-wash due to being intended for single use only.

Induction Decay Test (EN 1149-3: 2004 Method 2)

Determination of Induction Decay Time

	Shielding Factor (S)	Half Decay Time t_{50} (Secs)
1	0.00	>30.00
2	0.00	>30.00
3	0.00	>30.00
Mean	0.00	>30.00

Note: The fabric was not subjected to a pre-wash due to being intended for single use only.

SAMPLE D - HALYARD* PUREZERO* SMOOTH HG3 White Nitrile Gloves

Surface Resistivity Test (EN 1149-1: 2006)
Sample D

Determination of Surface Resistivity

The surface resistivity of 5 areas across the sample was determined according to the method specified in BS EN 1149-1: 2006

Surface	Surface Resistance (Ω)	Surface Resistivity (Ω)
Face	1.2×10^{12}	2.4×10^{13}
Face	1.4×10^{12}	2.8×10^{13}
Face	1.8×10^{12}	3.6×10^{13}
Face	1.8×10^{12}	3.6×10^{13}
Face	1.1×10^{12}	2.2×10^{13}
Mean	1.4×10^{12}	2.8×10^{13}
Reverse	1.0×10^{12}	2.0×10^{13}
Reverse	1.6×10^{12}	3.2×10^{13}
Reverse	1.1×10^{12}	2.2×10^{13}
Reverse	1.5×10^{12}	3.0×10^{13}
Reverse	1.9×10^{12}	3.8×10^{13}
Mean	1.4×10^{12}	2.7×10^{13}

Note: The fabric was not subjected to a pre-wash due to being intended for single use only.

Induction Decay Test (EN 1149-3: 2004 Method 2)

Determination of Induction Decay Time

	Shielding Factor (S)	Half Decay Time t_{50} (Secs)
1	0.00	9.37
2	0.00	7.85
3	0.00	13.05
Mean	0.00	10.09

Note: The fabric was not subjected to a pre-wash due to being intended for single use only.

SAMPLE E - HALYARD* PUREZERO* HG3 Light Blue Nitrile Gloves

Surface Resistivity Test (EN 1149-1: 2006)
Sample E

Determination of Surface Resistivity

The surface resistivity of 5 areas across the sample was determined according to the method specified in BS EN 1149-1: 2006

Surface	Surface Resistance (Ω)	Surface Resistivity (Ω)
Face	5.6×10^{11}	1.1×10^{13}
Face	5.0×10^{11}	9.9×10^{12}
Face	5.5×10^{11}	1.1×10^{13}
Face	5.3×10^{11}	1.0×10^{13}
Face	5.1×10^{11}	1.0×10^{13}
Mean	5.3×10^{11}	1.0×10^{13}
Reverse	7.0×10^{11}	1.4×10^{13}
Reverse	6.8×10^{11}	1.3×10^{13}
Reverse	6.7×10^{11}	1.3×10^{13}
Reverse	6.4×10^{11}	1.3×10^{13}
Reverse	7.2×10^{11}	1.4×10^{13}
Mean	6.8×10^{11}	1.3×10^{13}

Note: The fabric was not subjected to a pre-wash due to being intended for single use only.

Induction Decay Test (EN 1149-3: 2004 Method 2)

Determination of Induction Decay Time

	Shielding Factor (S)	Half Decay Time t_{50} (Secs)
1	0.02	6.09
2	0.01	5.57
3	0.00	7.74
Mean	0.00	6.47

Note: The fabric was not subjected to a pre-wash due to being intended for single use only.



Thank you for your interest in Halyard products. If you have any questions or need additional information, please do not hesitate to contact us at PIQ@hyh.com or call us directly at (844) 425-9273.

Sincerely,

A handwritten signature in black ink, appearing to read 'S.D.' with a long horizontal flourish extending to the right.

Steven Dowdley
Director of Regulatory Affairs
Global Products
O&M Halyard, Inc.

A handwritten signature in black ink, appearing to read 'Ryan Solan' in a cursive style.

Ryan Solan
R&D Senior Engineer
Global Research and Development
O&M Halyard, Inc.

*Registered Trademark or Trademark of O&M Halyard or its affiliates. ©2021. All rights reserved.

EU Type Examination Certificate

This is to certify that:

O&M Halyard Inc.
9120 Lockwood Blvd
Mechanicsville
Virginia
23116
USA

Holds Certificate Number:

CE 725272

In respect of:

**Nitrile Protective Gloves for Personal Protection.
Model CLN3031LG powder free gloves.**

on the basis that BSI carried out the relevant Type Examination procedures under the requirements with the Regulation (EU) 2016/425 of the European Parliament and Council relating to Personal Protective Equipment Regulation (PPE) Annex V (Module B) and meets the relevant health and safety requirements specified in Annex II

For and on behalf of BSI, a Notified
Body for the above Regulation
(Notified Body Number 2797):



Drs. Dave Hagenaaers, Managing Director

First Issued: 2020-11-09

Latest Issue: 2020-11-09

Effective Date: 2020-11-09

Expiry Date: 2025-11-09

Page: 1 of 4



...making excellence a habit.™

EU Type Examination Certificate

No. CE 725272

Product Specification

Range: Halyard Purezero HG3 White Nitrile Gloves Non-Sterile Ambi (TACKY)

Models: CLN3031XS
CLN3031SM
CLN3031MD
CLN3031LG
CLN3031XL

Classification: Protective gloves for use against chemical and micro-organism hazards.

Description: A five fingered, ambidextrous, single use powder free, non-sterile, Natural Rubber Latex with textured finger surface with tacky grip. Gloves are 310mm in length available coloured White.

PPE Category: Complex

Product sizes: XS, S, M, L, XL

Applicable The following Harmonized European Standards:

Standards: EN 420:2003+A1:2009 Protective gloves. General requirements.

EN ISO 374-1:2016. Protective gloves against dangerous chemicals and micro-organisms. Terminology and performance requirements for chemical risks.

EN 374-2:2019. Protective gloves against dangerous chemicals and microorganisms. Determination of resistance to penetration.

EN 374-4:2019 Determination of resistance to degradation by chemicals.

EN ISO 374-5:2016 Protective gloves against dangerous chemicals and micro-organisms. Terminology and performance requirements for micro-organism risks.

EN 16523-1:2015. Determination of material resistance to permeation by chemicals. Permeation by liquid chemical under conditions of continuous contact.

ISO 16604:2004 Clothing for protection against contact with blood and body fluids. Determination of resistance of protective clothing materials to penetration by blood-borne pathogens.

First Issued: 2020-11-09

Latest Issue: 2020-11-09

Effective Date: 2020-11-09

Expiry Date: 2025-11-09

Page: 2 of 4

This certificate has been issued by and remains the property of BSI Group The Netherlands B.V., John M. Keynesplein 9, 1066 EP Amsterdam, The Netherlands and should be returned immediately upon request.
To check its validity telephone +31 20 3460780. An electronic certificate can be authenticated [online](#).

BSI Group The Netherlands B.V., registered in the Netherlands under number 33264284, at John M. Keynesplein 9, 1066 EP Amsterdam, The Netherlands
A member of BSI Group of Companies.

EU Type Examination Certificate

No. CE 725272

Product Specification

Performance

General requirements for gloves to EN 420:2003+A1:2009

Characteristic	Level
Dexterity	5

Terminology and performance requirements for micro-organism Risks EN ISO 374-5:2016

Characteristic	Level
Protection against bacteria and fungi	Pass
Protection against viruses	Pass

Resistance to chemical permeation to EN ISO374-1:2016

Tested to the chemicals below to EN 16523-1:2015

Resistance to Degradation to chemical protection EN 374-4:2019

Tested to the chemicals below

Chemical	Permeation Level	Mean Degradation %
70% Isopropyl Alcohol	0	74.0
40% Sodium Hydroxide (K)	6	-12.1
50% Sulphuric Acid	6	-23.5
30% Hydrochloric Acid	6	22.7
1% Ethidium Bromide	6	-5.2

First Issued: 2020-11-09

Latest Issue: 2020-11-09

Effective Date: 2020-11-09

Expiry Date: 2025-11-09

Page: 3 of 4

This certificate has been issued by and remains the property of BSI Group The Netherlands B.V., John M. Keynesplein 9, 1066 EP Amsterdam, The Netherlands and should be returned immediately upon request.
To check its validity telephone +31 20 3460780. An electronic certificate can be authenticated [online](#).

BSI Group The Netherlands B.V., registered in the Netherlands under number 33264284, at John M. Keynesplein 9, 1066 EP Amsterdam, The Netherlands
A member of BSI Group of Companies.

EU Type Examination Certificate

No. CE 725272

Certificate Administration Details

Technical File Reference: No. 012-02 R01 Halyard Non-Sterile Cleanroom Gloves

Certificate Amendment Record:

Issue Date	Comments	Internal BSI Project Number
November 2020	First issue models: CLN3031XS, CLN3031SM, CLN3031MD CLN3031LG, CLN3031XL.	2797:20:3154546

Note: The Certificate holder is responsible for ensuring that the Notified Body is advised of changes to any aspect of the overall processes utilised in the manufacture of the product, failure to do so could invalidate the Certificate in respect of product manufactured following the introduction of such changes.

Monitoring of manufactured PPE:

The validity of the Certificate is also dependent on the maintenance of the EC quality of production by monitoring system, Module C2, as referenced on BSI Certificate CE 708082.

First Issued: 2020-11-09

Latest Issue: 2020-11-09

Effective Date: 2020-11-09

Expiry Date: 2025-11-09

Page: 4 of 4

This certificate has been issued by and remains the property of BSI Group The Netherlands B.V., John M. Keynesplein 9, 1066 EP Amsterdam, The Netherlands and should be returned immediately upon request.
To check its validity telephone +31 20 3460780. An electronic certificate can be authenticated [online](#).

BSI Group The Netherlands B.V., registered in the Netherlands under number 33264284, at John M. Keynesplein 9, 1066 EP Amsterdam, The Netherlands
A member of BSI Group of Companies.



TITLE: HALYARD* PUREZERO* HG3 Nitrile Gloves

PRODUCT UPDATE: AQL (Acceptable Quality Limit) improvement from AQL 1.5 to AQL 1.0

WHAT YOU NEED TO KNOW: For the lot release inspection of HALYARD* PUREZERO* HG3 Nitrile Gloves, the outgoing inspection acceptable quality level has been improved from AQL 1.5 to AQL 1.0 for freedom from holes/pinhole testing. All of the HALYARD* PUREZERO* HG3 Nitrile Gloves have passed the criteria for water tightness (pinholes) per the applicable ASTM and or EN test method/standards. There are no changes to the formulation, manufacturing process, or process specifications/parameters.

WHEN IS THIS CHANGING: These changes will be displayed on the product when it enters the market in January 2022.

WHERE TO FIND THIS CHANGE ON THE PACKAGING:

CASE LABEL:

AQL 1.0 Level 2 GI	ISO 374-5:2016 VIRUS	ISO 374-1/Type C K-Low Chemical
--------------------	-----------------------	----------------------------------

BAG/POUCH LABEL:

ACCELERATOR FREE* • LOW DERMATITIS POTENTIAL								
	STERILE R						Permeation Test EN 16523-1:2015	Degradation Test EN 374-4:2019
AQL 1.0 Level 2 GI	ISO 374-5:2016 VIRUS	ISO 374-1/Type C K-Low Chemical		Chemical	Breakthrough Time (min.)	Performance Level	Degradation %	
CE 2797 (PPE Cat. III)	halyardhealth.com/information	1	NaOH, 40%	>480	Class 6	-2.1		

IFU:

Manufactured at our SAFESKIN* Facility

							AQL 1.0 Level 2 GI	ISO 374-5:2016 VIRUS	ISO 374-1/Type C K-Low chemical EN ISO 374-1:2016+A1:2018	halyardhealth.com/information
--	--	--	--	--	--	--	--------------------	------------------------	--	--



ORDERING INFORMATION:

Product Name	Size	Code
HALYARD* PURERZERO* HG3 Light Blue Nitrile Gloves	XS	CLN9031XS
HALYARD* PURERZERO* HG3 Light Blue Nitrile Gloves	S	CLN9031SM
HALYARD* PURERZERO* HG3 Light Blue Nitrile Gloves	M	CLN9031MD
HALYARD* PURERZERO* HG3 Light Blue Nitrile Gloves	L	CLN9031LG
HALYARD* PURERZERO* HG3 Light Blue Nitrile Gloves	XL	CLN9031XL
HALYARD* PUREZERO* HG3 White Nitrile Gloves	XS	CLN3031XS
HALYARD* PUREZERO* HG3 White Nitrile Gloves	S	CLN3031SM
HALYARD* PUREZERO* HG3 White Nitrile Gloves	M	CLN3031MD
HALYARD* PUREZERO* HG3 White Nitrile Gloves	L	CLN3031LG
HALYARD* PUREZERO* HG3 White Nitrile Gloves	XL	CLN3031XL
HALYARD* PUREZERO* HG3 SMOOTH White Nitrile Gloves	XS	CLN3231XS
HALYARD* PUREZERO* HG3 SMOOTH White Nitrile Gloves	S	CLN3231SM
HALYARD* PUREZERO* HG3 SMOOTH White Nitrile Gloves	M	CLN3231MD
HALYARD* PUREZERO* HG3 SMOOTH White Nitrile Gloves	L	CLN3231LG
HALYARD* PUREZERO* HG3 SMOOTH White Nitrile Gloves	XL	CLN3231XL
HALYARD* PUREZERO* HG3 Sterile Light Blue Nitrile Gloves	6.0	CLN923260
HALYARD* PUREZERO* HG3 Sterile Light Blue Nitrile Gloves	6.5	CLN923265
HALYARD* PUREZERO* HG3 Sterile Light Blue Nitrile Gloves	7.0	CLN923270
HALYARD* PUREZERO* HG3 Sterile Light Blue Nitrile Gloves	7.5	CLN923275
HALYARD* PUREZERO* HG3 Sterile Light Blue Nitrile Gloves	8.0	CLN923280
HALYARD* PUREZERO* HG3 Sterile Light Blue Nitrile Gloves	8.5	CLN923285
HALYARD* PUREZERO* HG3 Sterile Light Blue Nitrile Gloves	9.0	CLN923290
HALYARD* PUREZERO* HG3 Sterile Light Blue Nitrile Gloves	10.0	CLN923210
HALYARD* PUREZERO* HG3 Sterile White Nitrile Gloves	6.0	CLN323260
HALYARD* PUREZERO* HG3 Sterile White Nitrile Gloves	6.5	CLN323265
HALYARD* PUREZERO* HG3 Sterile White Nitrile Gloves	7.0	CLN323270
HALYARD* PUREZERO* HG3 Sterile White Nitrile Gloves	7.5	CLN323275
HALYARD* PUREZERO* HG3 Sterile White Nitrile Gloves	8.0	CLN323280
HALYARD* PUREZERO* HG3 Sterile White Nitrile Gloves	8.5	CLN323285
HALYARD* PUREZERO* HG3 Sterile White Nitrile Gloves	9.0	CLN323290
HALYARD* PUREZERO* HG3 Sterile White Nitrile Gloves	10.0	CLN323210

Thank you for your interest in Halyard products. If you have any questions or need additional information, please do not hesitate to contact us at PIQ@hyh.com or call us directly at (844) 425-9273.

Sincerely,

Shannon Smith

Shannon Smith
Associate Product Manager
Global Products
O&M Halyard, Inc.

Steven Dowdley
Director of Regulatory Affairs
Global Products
O&M Halyard, Inc.

Ryan Solan

Ryan Solan
R&D Senior Engineer
Global Research and Development
O&M Halyard, Inc.